



Type

Configuration:
Spiral Wound

Membrane Polymer:
Composite Polyamide

Brine Spacer Material:
Polypropylene

Specifications

Permeate
Flow:
700 gpd
(2,6 m³/d)

Salt
Rejection:
99,3% nominal
(99,0% minimum)

Nominal Membrane
Area:
35ft²
(3,2m²)

Test Conditions

(After 30 min of operation)

Solution
NaCl
32000 ppm

Applied
Pressure:
800 psi
(56 bar)


Operating
Temperature:
77 °F
(25 °C)

Permeate
Recovery:
10%

pH
Range:
6,5 ÷ 7,0

Dimensions

A Total Length	B ATD Diameter	C Connection Diameter	D _F Core Tube Feed Side	D _C Core Tube Conc. Side	Weight
21.0 inches (533,4 mm)	3.95 inches (100,3 mm)	0.75 inches (19,1 mm)	1.2 inches (30,5 mm)	1.2 inches (30,5 mm)	4 lbs (1,8 Kg)



Maximum Operating Limits

Operating Pressure Fibreglassed	Temperature	Pressure Drop	Feed Flow	Chlorine Concentration	Feedwater SDI (15min)	Feedwater Turbidity
1000 psi (69 bar)	113 °F (45 °C)	10 psi (0,7 bar)	12 gpm (45,4 lpm)	<0,1 ppm	5,0	1,0 NTU

Other Operating Limits

Feedwater
pH
3,0 ÷ 10,0

Minimum ratio of concentrate to
permeate flow for any element
5:1

The limitations shown in Operating Limits are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

Notice: Minimum permeate flow for individual elements 15 percent below listed flow. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite.

Guidelines: Permeate obtained from first hour of operation should be discarded.

Avoid static permeate-side backpressure at all times.

These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale.

Please refer to the application information "technical bulletins" in our website (search: foulant, cleaning, storage, other) or contact us.

For element loading use only silicon or glycerine to lubricate o-rings and brine seal.

The customer is fully responsible for the effects of incompatible chemicals on elements. The presence of free chlorine and other oxidizing agents will cause membrane failure, the damaged is not covered under warranty.

Oltremare believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Oltremare assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Oltremare's products for the user's specific end uses.

No performance warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Consult factory for detailed warranty information.

We reserve the right to modify or amend specifications without prior notice.